

Coadd™ BP-6080

Surface Additive

DESCRIPTION

Coadd™ BP-6080 is a non-silicone mixture of surface-active polymers. The product is recommended for water-borne systems such as baking coatings, 2K PU coating and ambient curing systems. It prevents the formation of boiling marks and bubbles. It also gives good leveling performance, and has good compatibility with water-borne system.

PHYSICAL PROPERTIES

Appearance	Light yellow liquid
Density (g/ml)	0.95
Viscosity (25℃, mPas)	<200
Flash point (℃)	78

Note: These properties are only typical, and do not represent product specifications

APPLICATION CHARACTERISTIC AND ADVANTAGES

Coadd™ BP-6080 is recommended for water-borne baking coating systems, prevents the formation of bubbles and boiling marks., and avoid the formation of cratering and pinholes. The product also provides good leveling performance and good compatibility with resins. The product can be added in grinding, let down. or post addition, sufficient dispersing time is required when post addition.

Suggested dosage (base on the total formulation): 0.5 – 2.5%. Optimum level of dosage base on the laboratory testing.

SAFETY NOTICE

Before using the products, please refer to SDS for detailed safety data, handling and storage procedures recommended.

DISCLAIMER

It is common proposal for product usage and demand above information based on our professional knowledge. Due to environmental uncertainty and out of our control from practical process, please test and make evaluation ahead of use to ensure efficient and safe. For your reference, the above information is only for commonly know and use the product. It is guaranteed to meet quality and product specification.

****Please refer to SDS for more information**